



POLIPROPYLENE STRAPPING

Reggia in Polipropilene - Polypropylen Umreifungsband-Feuillard de cerclage en polypropylene -Fleje de polipropileno para flejar

DATA SHEET

Scheda tecnica - Datenblatt - Fiche de donnees - Hoja de datos

PRODUCT TYPE: <small>Tipo - Typ -Designation -Tipo</small>	15X0,85 HT
CORE (mm) : <small>Mandrino - Kern - Mandrin - Mandril</small>	400 X 160
Surface <small>Superficie - Oberflaeche - Surface -Superficie</small>	embossed <small>Goffrata - Gerpraegt- Goufrée - Grafilado</small>
meters/coil (m) <small>Metraggio/Bobina -Meter/Spule -Metrage/Bonine - Metros/Rollo</small>	1500 <small>± 2,5%</small>
WIDTH, <small>Larghezza -Breite - Lareur - Anchura</small>	Maximum, mm 15,00
	Nominal, mm 14,50
	Minimum, mm 14,00
	Maximum, mm ,89
THICKNESS, <small>Spessore - Dicke - Epaisseur - Grueso</small>	Nominal, mm ,85
	Minimum, mm ,81
GRAMM METER, <small>Grammo metro -Gramm meter - Gramme metre - Metro del gramo</small>	Maximum, gr. 8,90
	Nominal, gr. 8,50
	Minimum, gr. 8,10
	AVERAGE BREAKING STRENGTH, <small>Resistenza media - Durchschnittsreiffestigkeit - Résistance moyenne -</small>
	[N] 3502
ELONGATION AT BREAK, <small>Allungamento - Durchschnittsdehnung - Allongement - Alargamiento</small>	Maximum; % 25
	Nominal, % 20
	Minimum, % 15
QUALITY STANDARD <small>Qualità standard - Qualitätsstandard - Standard de qualite -</small>	UNI EN ISO 9001

Straps with the term "UV" only, are particularly protected against UV-rays effects.

Solo la reggia con dicitura "UV" è particolarmente protetta dall'azione dei raggi ultravioletti.

Baender ausschliesslich mit "UV" Bezeichnung, sind besonders geschuetzt gegen UV-Strahlen.

Solo el fleche con additivos "UV" puede esser protegida de los rayos ultravioletas.

Date of issue

Data - Ausgabedatum - Date - Fecha

29/01/2024